

CREAMY BLUSH

PHASE	INGREDIENTS	PROVIDER	INCI	(wt-%)
A	PURIFIED WATER		Water	48.10
	DIGLYCERIN S	Sakamoto Yakuhin Kogyo	Diglycerin	1.00
	HYDROLITE 5 GREEN	Symrise AG	Pentylene Glycol	3.00
	ADEKANOL GT-930	ADEKA	Polyurethane-59, Butylene Glycol, Water, Tocopherol	4.00
	KUNIPIA-F	Kunimine	Bentonite	0.500
B	S FACE IS-1001P	Sakamoto Yakuhin Kogyo	Polyglyceryl-10 Isostearate	3.00
	TAISET 50-C	Taiyo Kagaku	Glyceryl Behenate, Polyglyceryl-6 Octastearate	1.00
	REFINED CARNAUBA WAX N°1	Cerarica Noda	Copernicia Cerifera Wax	6.00
	SALACOS 334	Nisshin Oillio	Caprylic/Capric/Myristic/Stearic Triglyceride	5.00
	O.D.O	Nisshin Oillio	Caprylic/Capric Triglyceride	6.80
	PHYTOSQUALAN	Sophim	Squalane	7.00
	SALACOS HS-6C	Nisshin Oillio	Polyhydroxystearic Acid	1.00
C	MYRISTOYL PULLULAN	Katakura	Myristoyl Pullulan	1.00
D	TiO2 CR-50 ST-70%, S FACE IS-1009P-30%		Titanium Dioxide, Aluminum Hydroxide, Isopropyl Titanium Triisostearate, Polyglyceryl-10 Decaisostearate	4.30
	HP Iron Oxide Red ST-50%, S FACE IS-1009P-50%	K.S. Pearl + Sakamoto Yakuhin Kogyo	Iron Oxides, Isopropyl Titanium Triisostearate, Polyglyceryl-10 Decaisostearate	2.60
	HP Iron Oxide Yellow ST-45%, S FACE IS-1009P-55%			0.50
	SERICITE H	K.S. Pearl	Mica	3.00
E	METASHINE® MT1030TY	NSG	Calcium Aluminum Borosilicate, Titanium Dioxide, Iron Oxides	2.00
F	FRESH PEACH IV 78661	Kobayashi Perfumery	Fragrance	0.20
			Total	100,00

1/ Add phase A to main vessel, then heat to 75-85°C while stirring, to make homogeneous.

2/ Add phase B to another vessel, then melt by heating at 75-85°C.

3/ Add phase C to phase B, then homogenize using a dispersion mixer.

4/ Add phase B+C to the main vessel, then emulsify with dispersion mixer at 70-80°C.

5/ Add phase D to phase A+B+C, then homogenize using a dispersion mixer.

6/ After defoaming, fill the bulk into suitable containers.